Almath



The Complete Guide To Selecting The Right Material For Crucibles And Ceramic Components

www.almathcrucibles.com

TABLE OF CONTENTS

01 Industrial And Research Applications 03

02 High-Temperature Ceramics: Beyond The Brittle Myth 04

03 What Causes Crucible Failure? 05

04 Understanding Ceramic Crucible Performance 06

05 Material Selection Guide 07

06 High-Purity vs Standard Materials 10

07 Porous vs Fully Dense Ceramics 11

08 Design And Manufacturing Considerations 12

09 Application Examples 13

10 Contact Almath Crucibles Today 14

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Industrial And Research Applications

Selecting the correct materials for high-temperature environments is a critical engineering decision that dictates the safety and efficiency of your entire process. Whether you are working in a university laboratory or an industrial foundry, the performance of your ceramic components determines the success of your project. Choosing the wrong material often leads to a cracked crucible, contaminated samples, or unexpected production stops that can cost thousands in lost time and damaged equipment.

At Almath Crucibles, we act as a partner to your technical team. We help you understand the complex variables that affect ceramic performance so you can make choices that support your long-term goals. This guide bridges the gap between identifying a problem and selecting a reliable solution, ensuring reliable performance in demanding industrial environments.



CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

High-Temperature Ceramics: Beyond The Brittle Myth

One of the most common misconceptions about technical ceramics is that their brittle nature makes them unsuitable for complex engineering or high-stress environments. While it is true that ceramics do not deform like crack-tolerant metals, they offer unparalleled chemical resistance and thermal stability when designed correctly. Instead of viewing brittleness as a flaw, we treat it as a design parameter.





The key to working with ceramic components is to design around their natural properties. We achieve this by using radiused edges to distribute stress and by avoiding sudden, large changes in cross-sections that could create points of failure. While simple shapes are often the most reliable choice for high-heat applications, advanced manufacturing allows for more intricate designs. These can be produced via green machining before the material is fired, or through fired machining using precision diamond tools for parts that require exacting tolerances for detailed and complex assembly.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

What Causes Crucible Failure?

Understanding why a ceramic crucible fails is the first step toward preventing future issues and protecting your laboratory or facility. Failure is rarely random; it is usually a result of the incompatible environment.

1

Thermal Shock: This is the primary cause of failure. It occurs when a rapid change in temperature causes different parts of the material to expand or contract at different rates. If the heating or cooling rate is too fast, the internal stress will cause the component to fracture. A common example is heating a fully dense crucible too quickly or removing it from a furnace and exposing it to a sudden temperature change. The resulting thermal stresses can cause the crucible to crack unexpectedly.

2

Chemical Attack: Many materials become highly reactive at elevated temperatures. Slags and melts can be acidic or basic, and if the chemistry of the crucible does not match the contents, the material will eventually dissolve, erode, or degrade. For example, using an alumina crucible with highly basic materials can react with the crucible, causing contamination, loss of containment, or crucible weakness, whereas an MgO crucible would not react with the contents and avoid these issues.

3

Wetting And Penetration: Porosity is useful in preventing thermal shock, and many metals can be melted in porous crucibles, however if the material is reactive or has a high wettability the contents can penetrate the crucible. This may result in contamination of the batches or future batches, particularly where material purity is critical.

4

Incorrect Usage: Sometimes a failure occurs because it is used incorrectly, this maybe because it is used in the incorrect atmosphere, its max temperature is exceeded, or because it experiences a high load below its maximum no load temperature. Almath’s engineers are able to offer advice on the correct crucible materials for your application, and any precautions you may require.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Understanding Ceramic Crucible Performance

When assessing how a material will perform, we look at several core factors that go beyond simple dimensions. The most immediate is the ceramic crucible melting point, which dictates the absolute limit of the material. However, the maximum no load temperature is often lower to ensure mechanical integrity over time.



Mechanical strength and chemical resistance are equally important. You need a component that can withstand the weight of the melt and the corrosive nature of the chemicals involved.

By understanding the alumina crucible temperature range or the specific limits of zirconia, you can match the material to the exact requirements of your process. This level of precision reduces the risk of equipment failure and allows your researchers and engineers to work with complete confidence.

Material selection should also consider operating atmosphere, heating and cooling rates, purity requirements, and the potential for chemical interaction between the crucible and its contents. These factors often have just as much influence on performance as temperature alone.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US



Material Selection Guide

Choosing between alumina, zirconia, and other specialised materials depends on your peak temperature and the chemical nature of what you are melting.

The table on the next page provides a high-level comparison of the most commonly used crucible and ceramic component materials. Final material selection should always consider factors such as operating temperature, heating rate, chemical compatibility, purity requirements, and the process atmosphere.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Material	Typical Maximum Working Temperature	Thermal Shock Resistance	Chemical Resistance	Typical Applications
Alumina	Up to ~1600°C	Moderate	Good resistance to many acids and alkalis	General laboratory work, metal melting, research applications
Zirconia	Above 1600°C (depending on grade)	Good	Excellent resistance to acidic materials and corrosive environments	High-temperature processing, corrosive melts, specialist industrial applications
Magnesium Oxide (MgO)	Above 2000°C	Moderate	Excellent resistance to basic/alkali materials, poor resistance to acidic materials	Metallurgy, battery materials, molten salts, rare earth processing
Boron Nitride	Up to ~900°C in air, up to ~2000°C in vacuum or inert atmospheres	Excellent	Non-wetting to many molten metals and materials	Semiconductor processing, specialist melting applications, high-purity environments
Quartz	Up to ~1200°C	Excellent	Good chemical purity and resistance to thermal shock	Semiconductor manufacturing, analytical laboratories, high-purity applications

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Alumina: Alumina crucibles are the industry standard for a reason. They are cost-effective, offer high strength, and provide excellent resistance to both acids and bases. They typically have a maximum working temperature around 1600°C. For those requiring the highest levels of purity, to avoid trace element interference, high-purity alumina crucibles are the preferred choice for sensitive analysis and long life.

Zirconia: When your process goes above 1600°C, a zirconia crucible is often required. Zirconia is available in various grades and offers exceptional resistance to chemical attack, particularly from acidic materials. It is also known for its high mechanical strength, making it ideal for high performance components. Some grades of zirconia (optimised for strength rather than temperature resistance) are excellent for high performance components. Depending on the stabilisation system used, zirconia can operate above 2000°C while maintaining excellent chemical resistance.

Magnesium Oxide (MgO): MgO is the specialist choice for basic slags. While it does not perform as well against acids, its ability to withstand basic environments at temperatures over 2000°C makes it indispensable for specific metallurgical processes where other ceramics would fail. MgO offers a cost effective alternative to zirconia when alumina does not offer the required performance.

Boron Nitride: A boron nitride crucible is excellent for non-wetting applications and provides superb thermal shock resistance. We often recommend a boron nitride crucible when the contents must be easily removed after cooling without sticking to the walls. However, it is limited to around 900°C in air, but up to 2000°C in vacuum or inert atmospheres.

Quartz: A quartz crucible is ideal for applications requiring high purity and excellent resistance to thermal shock at more moderate temperatures. Because a quartz crucible is made of high-purity silica, it is a staple in semiconductor manufacturing and high-end laboratory research.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

High-Purity vs Standard Materials

The difference between a high-purity crucible and a standard grade is often found in the trace-level impurities that reside at the microscopic level. In standard refractories, these impurities often gather at the grain boundaries. When subjected to high temperatures and aggressive chemicals, these are the areas that are attacked first, leading to premature wear.



Using a high-purity crucible ensures better chemical resistance and prevents sample contamination. In some technologies such as battery materials, even a few parts per million of a detrimental element can ruin a batch.

Investing in high-purity materials is a way to ensure your results are accurate, and maximise the life of the crucible. We ensure our materials meet the stringent requirements of the most demanding technical buyers globally.






CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Porous vs Fully Dense Ceramics

Porosity is a design tool that affects nearly every property of advanced ceramic components, from their strength to their electrical properties.



Fully dense ceramics have no open porosity, making them highly resistant to chemical attack and physical wear. Because there are no pores for the melt to penetrate, they are easier to clean, provide better mechanical strength under load, and have less surface area for chemical attack. However, **their density makes them more susceptible to thermal shock**, meaning they must be heated and cooled slowly (no more than 5°C/min).



Conversely, a porous crucible is specifically designed to handle rapid temperature changes. The small voids within the material slow crack growth, allowing the ceramic to expand and contract more freely. While a porous crucible is better for thermal shock resistance, it can be more prone to chemical penetration and attack by some materials. Fortunately, most metals that are heated rapidly by induction melting do not wet and penetrate the crucible. This makes them ideal for the casting and refining of high value metals.

Choosing the right balance between density and porosity is essential for the long-term success of your ceramic crucibles and components.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Design And Manufacturing Considerations

When moving from standard shapes to bespoke ceramic components, manufacturing limitations must be considered to keep projects on track. We generally aim to avoid extensive fired machining because technical ceramics are incredibly hard and take a long time to process with diamond tools.

Green machining is a more efficient way to create custom ceramic components, though we must account for material shrinkage during the firing process. For parts requiring extreme precision, fired machining can achieve tolerances down to +/- 0.005 mm.



Almath has multiple ceramic forming methods to facilitate the manufacture of crucibles and ceramic components. The choice of manufacturing route is affected by the number of parts, the overall size, wall thickness and geometry of the parts required. Thin walled or uniform sections are often produced using slip casting, particularly if the parts are small (<40 mm) and small quantities are required (<30 off). Isostatic pressing can be used for much larger parts, thicker walls and has the advantage of being able to be machined before firing and the option of manufacturing products from thermal shock resistant materials. Isostatic pressing applies pressure to the powder uniformly, reducing residual stress and reducing the likelihood of failure. Almath’s engineers are on hand to review drawings and advise customers on the most appropriate manufacturing route for your product.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US

Application Examples

Our advanced ceramic components and high-purity vessels support a wide range of industrial and research applications:

1. **Green Steel:** Facilitating the transition to carbon-neutral metal production by providing chemically-resistant components for new smelting technologies.

2. **Biomedical:** Creating high-purity environments for the synthesis of artificial bone and joint materials where contamination is not an option.

3. **Precious Metal Refining**: Providing reliable casting, refining and assaying vessels for gold, silver, and platinum.

4. **Battery Materials:** Supporting high-purity processing and testing for the next generation of energy storage solutions.

5. **Nuclear and Aerospace:** Delivering custom ceramic components that must not fail under extreme heat, pressure, and radiation.

Every application has different requirements relating to temperature, atmosphere, purity, thermal cycling, and chemical compatibility. Our technical team works with customers to assess these factors and recommend the most appropriate material and manufacturing route for long-term performance.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US



Contact Almath Crucibles Today

Speak to an Almath ceramics specialist about selecting the right material, component, or manufacturing method for your application. Our UK-based manufacturing and technical mastery ensure you receive the superior quality, traceability, and rapid support your precision work demands.

CONTACT US

www.almathcrucibles.com sales@almath.co.uk 01638 591828

FOLLOW US